

Q-Slope Studies at Fermilab: New Insight From Cavity and Cutouts Investigations

A. Romanenko
Fermilab


- **New experimental findings on Q slopes**
 - Decomposition of the components of surface resistance (R_{BCS} and R_{res})
 - Shows which Q slope is due to what component
- **New superconducting measurements**
 - Low energy muon spin rotation
 - Baked/unbaked cutouts
 - N doped
- **New proximity effect model of the high field Q slope**
 - Evidence from cryogenic TEM investigations in cutouts
- **New model of the 120C baking**
 - Vacancy-based 120C baking mechanism and supporting evidence from cutouts
 - Suppression of the second phase of hydrides in direct observations
- **Conclusions**

- Using different temperature dependence to deconvolute the components of average surface resistance at ALL fields


$$R_s(T) = R_{\text{BCS}}(T) + R_{\text{res}}$$

Due to thermally excited
quasiparticles

Non-T-dependent,
saturation value at
 $T \rightarrow 0$




Measure $Q(E_{acc}, T)$ at many different $T < 2.17K$ and E_{acc}




Can be fitted using both approximate formula $R_{BCS}(T) = A/T \exp(-\Delta/kT)$, and by more precise BCS calculation based on Halbritter's program – virtually no difference in the results


A. Romanenko and A. Grassellino, Appl. Phys. Lett. 102, 252603 (2013)

A. Romanenko and A. Grassellino, Appl. Phys. Lett. 102, 252603 (2013)




A. Romanenko and A. Grassellino, Appl. Phys. Lett. 102, 252603 (2013)






Field dependence of R_{BCS} may be explained by the expected changes of pairing potential $\Delta = \Delta(H)$ in clean (unbaked) and dirty (120C baked) limits





Instead of modeling the full temperature transfer with only $R_s = G/Q_0$ as an input use temperature mapping to measure the outside wall temperature

Negligible effect on R_{BCS} at $T \leq 2\text{K}$

More – hot topic session on Thursday





T-map data shows that local surface resistance in HFQS regime is highly correlated to R_s at lower fields (MFQS)



More info – please see [\[A. Romanenko et al, TUP101\]](#)


- High field Q slope is due to residual
 - Not SC gap closing, thermal feedback etc.
- Medium field Q slope is a combination of R_{BCS} and R_{res}
 - Not due to the difference in T_{rf} and T_{bath}
 - Correlation between high and medium fields in unbaked cavities
- Low field Q slope is likely due to residual

- Bulk muon spectroscopy
 - A. Grassellino et al, TUP031
- Low energy muon spectroscopy
 - A. Romanenko et al, TUP038
- Bitter decoration
 - F. Barkov et al, TUP016







$$N(t) = N_0 \exp(-t/\tau_\mu) [1 + a G(t)] + \text{Bkg}$$

Contains physics




$$\omega_\mu(z) = \gamma_\mu B_{\text{loc}}(z)$$

Frequency – field amplitude
Damping – field non-uniformity



$$\omega_{\mu}(z) = \gamma_{\mu} B_{\text{loc}}(z)$$


Use variable energy muons, which stop in the first ~100nm



BCP and EP unbaked \rightarrow strong screening, excellent fit provided by the clean limit Pippard/BCS model

EP+120C bake \rightarrow strongly suppressed m.f.p., gradient of the m.f.p. from the surface, dirty limit

N-doped \rightarrow intermediate m.f.p., no gradient






Fit by Gaussian model for the field at the muon site – approximate, qualitative comparison

- Main element: presence of small proximity effect coupled nanohydrides within the penetration depth
 - Q disease “in miniature”
- Consistent with all experiments, provides quantitative description
- Falsifiable
 - Testable predictions

A. Romanenko, F. Barkov, L. D. Cooley, A. Grassellino, Supercond. Sci. Technol. 26 (2013) 035003

Near-surface H-rich layer is still there
after standard H degassing treatments




Integrate the H diffusion over the time
spent in the precipitation temperature
range $T < 160\text{K} \Rightarrow L > 1\text{ }\mu\text{m}$




All free near-surface H will
precipitate into hydrides

Not 120C baked sample





Note drastic change in the hydrogen-related m.f.p.

- Normal conducting hydrides of size d are superconducting by proximity effect up to the field $H_b \sim 1/d$




- Excellent fits



A. Romanenko, F. Barkov, L. D. Cooley, A. Grassellino, Supercond. Sci. Technol. 26 (2013) 035003


- So what happens with 120C bake?

A. Romanenko, C. J. Edwardson, P. G. Coleman, P. J. Simpson, *Appl. Phys. Lett.* **102**, 232601 (2013)




Large grain

BCP




EP

- Positron annihilation spectroscopy: 120C baking results in “doping” of the first ~50 nm from the surface with defects, most likely vacancies
 - EP itself introduces some vacancies in ~1 μm – may be the reason for more efficient 120C baking in EP cavities



A. Romanenko, C. J. Edwardson, P. G. Coleman, P. J. Simpson, Appl. Phys. Lett. **102**, 232601 (2013)

Cooling down of 120C baked niobium




Note no change in the hydrogen-related m.f.p. – remains low

- Direct imaging of the cross-sections of cavity cutouts in cryo-TEM [see Y. Trenikhina et al, TUP043]


Cold: 120C in situ bake for 48hours

Hot: no such bake



Heating: comparison of "cold" and "hot" spots


Cutout (d=11mm, t=3mm) sample on SEM post




FIB prep sample for TEM

"useful area"

SEM




Look at this area with subnanometer resolution in TEM at room **AND** $T < 100K$ temperatures




See also R. Tao et al, J. Appl. Phys. **114**, 044306 (2013) and TUP042 for cryoimaging of H-reach Nb samples

Y. Trenikhina et al, TUP043

NED at room T **Hot** and **Cold** spot: NO additional reflections, just Nb




Hot spot NED at **94K**: low T phase(s) along with Nb




“Statistics” of the second phase appearance: 44%-68% of the probed spots

F. Barkov et al, TUP014

Growing of hydrides at $T=160\text{K}$ in a mechanically polished sample





- Second phase (lower concentration, lower temperature) forms at 100K
 - NOT observed on 120C baked samples

- Both residual and BCS surface resistances carry a field dependence
 - Analysis of Q slopes should only be done on components
- Mean free path/ Meissner screening is lowest, depth-dependent in 120C baked material, highest in unbaked, N-doping leads to the “intermediate” situation
- Nanohydrides may be an omnipresent entity not appreciated before
 - May be THE cause of the high field Q slope
 - Proximity-induced superconductivity breaks down at lower fields than host (Nb)
 - May be related to the residual resistance field dependence
 - Dominant source of the medium field Q slope in unbaked cavities
 - Absence of nanohydrides may be behind the effect of doping
 - Plausible mechanism of 120C baking -> trapping of hydrogen by vacancies -> preventing/decreasing size of nanohydrides

- FNAL: F. Barkov, A. Grassellino, A. Crawford, D. Sergatskov, O. Melnychuk, R. Pilipenko
- IIT/FNAL: Y. Trenikhina
- IIT: J. Zasadinski
- Univ. of Chicago: S. Antipov
- Cornell Univ.: H. Padamsee